



JOUBERT POPLY

Poplar throughout - Face veneers II/III

Gluing class 2 or class 3 - E1

Light colour and light material.

Interior layout.

Wall facings, manufacture of furniture, packing cases.



TECHNICAL INFORMATION

GENERAL INFORMATION

Compliance of plywood with European norms:

- Gluing class: according to EN 314-2
- Faces classification: according to EN 635-2
- Dimension tolerance: according to EN 315
- Panel marking: according to EN 636
- Use class 2: according to EN 335

SPECIFICATIONS

Thicknesses: 4 to 30 mm.

CE2+ marking for structural use (according to EN 13986) for panels with a thickness ≥ 8 mm (control certificate delivered by FCBA).

CE NS marking for non-structural use (according to EN 13986) for panels with a thickness < 8 mm or gluing class 3.

Density:	450 kg/m ³ (± 50 kg/m ³)
Fire reaction:	D-s2, d0 for thicknesses ≥ 9 mm* E for thicknesses < 9 mm*
Formaldehyde emission:	Class E1 US EPA TSCA Title VI - CARB ULEF
Heat conductivity:	$\lambda = 0,11$ W/m.k
Pentachlorophenol content:	< 5 ppm

* Depending on how the panel is installed.

Thickness mm	Sizes cm
4	GLUING CLASS 2
5	250 x 122
6	252 x 185
8	310 x 153
9	
10	GLUING CLASS 3
12	250 x 122
15	252 x 185
18	310 x 153
20	
22	
25	
30	

For PEFC™-certified panels, depending on available credits, contact us.